

Durabrick

FAST SETTING IDEAL FOR BRICK AND BLOCK MAKING

LAFARGE
Building better cities™



Durabrick 32,5 R

is a product introduced by Lafarge South Africa to meet the specific requirements of brick and block makers and extend its wide range of innovative products.

This product has been formulated to meet the needs of brick and block makers. The benefits include:

- Good early age demoulding strength
- Improved compaction
- Improved brick and block surface texture
- Good workability














Guidelines for a mix

A standard builder's wheelbarrow that holds 65 litres of material is generally used to measure out the correct volumes of cement, stone and sand required to make a batch of concrete. DuraBuild is supplied in 50kg bags for use in a wide range of smaller jobs, as indicated in the mix proportions tables below. 2 x 50kg bags (often still referred to as 'pockets') are equivalent in volume to one wheelbarrow load.

Note: If you want to make a smaller batch of concrete, remember to use the same size container (for example a bucket) to measure all the ingredients. (Using a shovel to measure materials is not recommended because you cannot judge the quantities accurately.)



RECOMMENDED MIX PROPORTIONS BY VOLUME USING DURABRICK 32,5 R

	Cement	Sand	Stone
Brick and block making with crusher sand	2 	8 	-
Brick and block making optimised with crusher sand	2 	9 	-
Brick and block making with dump ash	2 	6 	-
Brick and block making optimised with dump ash	2 	7 	-
Mortar for bricklaying and plastering	2 	6 	-
Home Concrete 10-15 MPA Foundations, footings, domestic floors (un re-inforced)	2 	3.5 	3.5 

Safety when handling cement

Before starting any job, make safety the first step in your planning. Cement is such a commonly available product that many people use it without giving any thought to personal protection. It is important to take sensible handling precautions.

FOR FURTHER INFORMATION, SAFETY DATA SHEETS ARE AVAILABLE FROM:

- Your local building materials supplier
- Customer service centre on 0860 109 275 or 011 657 1111
- Lafarge website: www.lafarge.co.za

FOR BRICK AND BLOCK OPTIMISED MIXES CONTACT "ASK FOR THUSO" ON:

Toll Free: 0800 000 959